

## APP Klarlack UHS 410/APP Klarlack UHS 410 Harter

Two-component low-emission, quick drying acrylic Premium class clearcoat. It features with high content of solids up to 59% and VOC below 410 g/L. It offers very good levelling properties, easy application and polishing. It ensures high gloss and base coat colour fastness.



### QUICK APPLICATION- VERY SHORT DRYING TIME

Shortens significantly paint booth operation time:

Ready for assembly at temp.	
+20 °C	– 2,5 h.
+60 °C	– 15 min
IR radiator	– 10-15 min



Application without thinner !

Does not require an elasticizing additive during application on plastic.

High gloss.

Easy polishing.



APP UHS 410 New Formula clearcoat features with resistance to weather conditions in different climatic zones.


Specially designed resins provide lacquer resistance to stone related chipping and other fine damages.



Compatible with both Quick and Standard hardener depending on ambient temperature and area of application.



**1** Mixing ratio by volume



**2:1**

APP Klarlack UHS 410  
New Formula  
with hardener  
APP Klarlack UHS Harter

**2** Coats qty



**2x1** (50-60 µm)

**3** Application with spray gun




Ø **1,2-1,4**

**4** Evaporation time between coats



**5-10 Min**

**5** Pressure



**2,0-2,5 Bar**

ADVANTAGES

+  
EASY  
APPLICATION

+  
APPLICATION  
WITHOUT  
HARDENER

+  
HIGH GLOSS AND DEPTH OF  
DARK COLORS

+  
SMOOTH APPLICATION  
ON PLASTIC ELEMENTS  
without an elasticizing  
additive.

+  
HIGH STRENGTH  
Resistant to stone  
related chipping and other  
fine damage.

+  
MATERIAL SAVINGS  
15-20% comparing  
to standard lacquers

**CONTENT OF SOLIDS UP TO 59%.  
VOC 420 g/L**

APP No.	Product Description	Volume	Type	Bulk package
020137	APP Klarlack UHS 410	1L	Clear	6 items
020138	New Formula	5L		3 items
020335	APP Harter Klarlack UHS 410	0,5l	Standard	6 items
020336		2,5L		3 items
020337	APP Harter Klarlack UHS 410	0,5l	Quick	6 items
020338		2,5L		3 items