

TECHNICAL INFORMATION

Preparation Date:
19.03.2013.



Revision Date:
19.03.2013.

Page 1 from 1

Product Name: Rear View Mirror Assembly Adhesive SPL 99 - APP No. 040504

DESCRIPTION: a single component structural adhesive APP No. 040504 purposed for mounting the rear view mirror.

APPLICATION:

- Remove the remainder of old adhesive,
- Surfaces to be bonded must be clean, dry and degreased,
- Cut the mesh according to dimensions and shape of surface e.g. mirror support or grip,
- Apply an appropriate amount of adhesive (Care is required to avoid excess adhesive) to the metal surface and place the mesh upon the surface,
- Join and press together for 1 minute,
- Full bond strength takes 24 h to develop,

Packaging: 1 ml syringe

USE:

- Bonding of metal parts to glass and ceramic surfaces.
- Perfect for mounting the rear view mirror to windshield or towel metal grips.

Component	Methacrylate
Colour	Amber
Viscosity	2200-3000cP
Time of initial hardening with mesh	< 60 sec.
Time to achieve initial bond strength	~15 min.
Ambient temperature	-50~+13°C
Max gap	0.3 mm

The above information is based on currently available data and knowledge on the product and its use. The information does not purport to be a description of product in terms of its quality, fitness for use in some conditions, nor does it guarantee any particular features. User shall follow instructions provided on labels and MSDS. Manufacturer is not responsible for consequences and work effects that were influenced with factors beyond his control.