

# SPECIFICATIONS

Prepared on:  
May 10, 2005




Updated on:  
May 10, 2005

Page 1 of 1

## Product name: APP hard insulating mat

**DESCRIPTION:** Self-adhesive laminated material consisting of a mix of bitumen, elastomers, and fillers of various granularity.

<b>Characteristics:</b>	
Surface finish	polyethylene
Finish on the side coated with adhesive	self-adhesive protected with coated sheathing
Density	1.8-2.0 g/cm <sup>3</sup>
Weight per m <sup>2</sup> (standard)	4-10 kg/m <sup>2</sup>
Weight tolerance	± 10%
Combustion rate (in compliance with DIN 75200)	<20 mm/min
Combustibility (in compliance with FM VSS . 302)	SE
Immediate adhesion grip (in compliance with ASTM D 31211)	< 10 cm
Cohesion of adhesion (in compliance with FINAT8)	> 4 hours
Working temperature range (after applying)	-20/+80 °C
<b>Usage:</b>	Sound insulating material designed for use in a vertical and diagonal position, on flat or slightly curved surfaces exposed to vibrations.
<b>Base:</b>	
Proper base types:	Bases with various finishes, which are dry, free from oil, grease and other soiling.
Base preparation: 	Before attaching the mat, clean the surface and degrease it using W900 remover.
<b>Application:</b>	
Applying	Apply at room temperature.
Coverage	After removing the protective foil, the material is coverable with typical finishing products.
<b>Storage:</b>	Store at a temperature ranging from +10°C to +30°C in a dry and well-ventilated place.
<b>Industrial safety regulations:</b>	See: information on product labels. Users should observe all industrial safety regulations applicable in their countries.

The above information complies with current knowledge on our products and their possible applications. This guarantees no specific properties or usability in particular conditions. Users should observe guidelines and warnings provided on product labels and specified in material safety data sheets. We hold no responsibility if conditions beyond our control affect the final result of work.

Auto Plast Produkt Sp. z o.o. [Ltd.] 62-300 Września, ul. Przemysłowa 10, Poland  
tel. + 48(prf)61 437 00 00